

X-Gen Nitrile Exam Gloves
Chemical Resistance & Barrier Guide
Cat# 44-100

Chemical	Nitrile
ACETALDEHYDE	P
ACETIC ACID	G
ACETONE	F
ACETONITRILE	F
ACRYLIC ACID	G
AMYL ALCOHOL	E
BENZENE	F
BUTYL ACRYLATE	P
CHROMIC ACID	F
DIACETONE ALCOHOL	G
DIESEL FUEL	E
DIISOBUTYL KETONE	G
ETHANOL	F
FORMALDEHYDE, 30-70%	E
FORMIC ACID	G
FREON 113 OR TF	E
GLUTARALDEHYDE, <5%	G
GLYCEROL	E
HEXANE	E
HYDROCHLORIC ACID, <30%	G
HYDROCHLORIC ACID, 30-70%	G
HYDROFLUORIC ACID <50%	E
ISOBUTYL ALCOHOL	E
ISOPROPYL ALCOHOL	E
JET FUEL, <30% AROMATICS 73-248C	G
KEROSENE	E
METHANOL	F
N-PROPYL ALCOHOL	E
NITRIC ACID, <30%	E
PHENOL, >70%	G
PHOSPHORIC ACID, >70%	E
SILVER NITRATE	G
SODIUM CHLORIDE	E
SULFURIC ACID, 30-70%	F
XYLENES	F

(P) Poor (F) Fair (G) Good (E) Excellent